

DAP™-AM Series

Daido Alloy Powder – for Additive Manufacturing

SUS316L

The metal powder with high flowability suitable for additive manufacturing by SLM

Characteristics

SUS316L is an austenitic stainless steel with excellent ductility and toughness. It is suitable for prototype modeling, because of its high corrosion resistance and excellent formability.

Major applications

General machinery parts

Typical chemical composition

Typical chemical composition (mass%)					
C	Si	Mn	Ni	Cr	Mo
0.016	0.8	0.2	12	17	2.5

Particle size

Particle size (μm)
-53/+25

Physical properties*¹

Density (g/cm ³)	Specific heat (J/(kg · K)) [cal/g · K]				Linear expansion coefficient (×10 ⁻⁶ /K)				Thermal conductivity (W/(m · K))			
	24°C	100°C	200°C	300°C	28~100°C	28~200°C	28~300°C	28~400°C	24°C	100°C	200°C	300°C
7.86	559 [0.134]	604 [0.144]	608 [0.145]	600 [0.143]	15.0	16.4	17.1	17.7	16.0	18.1	19.5	20.4

*¹ Specimen heat treatment ST:1050°C/1h, WQ

Mechanical properties

	Status	YS* ² (MPa)	TS* ² (MPa)	Elongation* ² (%)	Reduction of area* ² (%)
DAP™-AM SUS316L	As 3D-printed	573	674	34	60
	Solution treated* ³	377	614	43	62
ASTM A182	Solution treated* ⁴	≥170	≥485	≥30	≥50

*² Tested temperature : RT, Tested specimen : JIS No.14A, Point distance : 25mm, Parallel area diameter : 5mm, Testing method : JIS Z 2241-2011 Standard

*³ Additive manufacturing-Removing from base plate-ST(1050°C/1h, WQ)-Machining-tensile test

*⁴ ST: Water-cooled after holding at 1040°C



DAIDO STEEL CO., LTD.

Tokyo Head Office Daido Shinagawa Building, 6-35, Konan 1-chome, Minato-ku, Tokyo, 108-8478 TEL +81-3-5495-1284
(Metal Powder Marketing & Sales Sect. Metal Powder Dept.)

Nagoya Office 10, Ryugu-cho, Minato-ku, Nagoya, Aichi, 455-0022 TEL +81-52-694-0776

Web site: <https://www.daido.co.jp/en/products/powder/index.html> Email address: funmatsu@ask.daido.co.jp

DAP is a trademark or a registered trademark of Daido Steel Co., Ltd.

■Disclaimer and copyright

The figures in this document are typical values based on the results of our tests and there is no guarantee that the figures presented will be achieved when the products are used. The information in this document is subject to change without notice. Please contact us for the latest information. Any unauthorized distribution or reproduction of the content of this document is prohibited.

WC2203 23.0,0(DDD)